

Laser+[®] RF (AF626)

Product Data Sheet

Application/Uses

- APET and thick sheet
- Beverage Packaging
- Bottles
- Custom Containers
- Refillable Bottles
- Sealing layer for CPET trays
- Thick wall containers

Product Description

Laser+[®] RF AF626 is produced at DAK Americas manufacturing site in Zarate, it is PTA/IPA based, and is sold to customers in Argentina, Bolivia, Brazil, Chile, Colombia, Mexico, Paraguay, Peru, Uruguay and Venezuela. DAK Americas Laser+[®] RF AF626 will be used primarily for thick wall applications such as refill bottles for water and carbonated soft drinks.

Sales Specifications

SPECIFICATION N°: AF626-1
EFFECTIVE DATE: January 10, 2009

This specification describes a grade of clear copolyester in the form of pellets which must meet all of the requirements listed below when tested as directed by the referenced methods.

Property	Value	Test Method
Intrinsic Viscosity	0.80 +/- 0.02	VGAS-A-AN-G-V-1 (or equivalent)
Color: CIE L* CIE a* CIE b*	78 minimum -3.50 to -0.5 -2.5 to 1.5	VGAS-A-AN-G-RS-0001
Fines	0.05 wt % maximum	VGAS-A-AN-G-GA-1 (or equivalent)
Acetaldehyde	1 ppm maximum, residual	VGAS-A-AN-G-GC-2

Product shipments are not tested for acetaldehyde. Samples that are representative of product are tested in a monitor program to ensure that the process capability for acetaldehyde in the polymer is less than the specification limit.

For reasons of safety and accuracy, the person performing methods described herein must be thoroughly trained and under the supervision of a professional person who is knowledgeable in the relevant science. Equipment and materials described should be used in accordance with safety precautions recommended by their manufacturers.

Typical Properties

Property ^a	Test ^b Method	Typical Value, Units ^c
Pellet Properties		
Crystalline Density	D 1505	1.35 g/cm ³
Bulk Density		
Poured	D 1895	805 kg/m ³ (50 lb/ft ³)
Vibrated	D 1895	880 kg/m ³ (55 lb/ft ³)
Melt Density @ 285°C (545°F)	D 1238 (Note A-Table 2)	1.29 g/cm ³
Crystalline Peak Melting Point (T _m) ^d	D 3418	242°C (467°F)
Heat of Fusion ^e	E 793	59 kJ/kg (14 cal/g)
Specific Heat ^e		
@ 23°C (73°F)	E 1269	1.0 kJ/kg·K (0.24 Btu/lb·°F)
@ 80°C (176°F)	E 1269	1.3 kJ/kg·K (0.31 Btu/lb·°F)
@ 100°C (212°F)	E 1269	1.4 kJ/kg·K (0.33 Btu/lb·°F)
@ 200°C (392°F)	E 1269	1.8 kJ/kg·K (0.43 Btu/lb·°F)
@ 280°C (536°F)	E 1269	2.1 kJ/kg·K (0.50 Btu/lb·°F)
Pellet Size		2 x 2 x 3 mm (.1x.1x.1 in.)
Pellet Shape		Rectangular

^a Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

^b Unless noted otherwise, the test method is ASTM.

^c Units are in SI or US customary units.

^d Determined by DSC on the second heating cycle.

^e Determined by DSC on the first heating cycle.

Specific heat in cal/g°C is numerically equivalent to the value in Btu/lb°F.

Comments

Properties reported here are tentative data based on testing of one lot of this material, and therefore may or may not be representative of average lots. DAK Americas makes no representation that the material in any particular shipment will conform exactly to the values given.

Caution: Do not use in medical applications involving permanent or temporary implantation in the human body. For other applications, see "DAK Medical Caution Statement" or the Material Safety Data Sheet for this product.

DAK Americas Argentina S.A. and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.