

## Product Data Sheet

### Eastman™ Cellulose Acetate Propionate (CAP-504-0.2)

#### Application/Uses

- Nail care
- Printing Inks

#### Product Description

Eastman™ Cellulose Acetate Propionate (CAP-504-0.2) is a free-flowing powder having low odor, low color, and high hydroxyl content. It is fast dissolving, has good water tolerance and resistance to souring, and is compatible with many ink resins and solvents. It has good resistance to discoloration from UV light and has good adhesion to plastics. It has a low viscosity (0.2 seconds) and has an approximate propionyl content of 42.5 wt%.

#### Typical Properties

Property	Typical Value, Units
Acetyl Content	0.6 wt %
Propionyl Content	42.5 wt %
Hydroxyl Content	5 wt %
Melting Point	188-210°C
Viscosity <sup>a</sup>	0.76 poise
Glass Transition Temperature (T <sub>g</sub> )	159°C
Tukon Hardness	20 Knoop
Wt/Vol	1.26 kg/L (10.53 lb/gal)

<sup>a</sup> Viscosity determined by ASTM Method D 1343. Results converted to poises (ASTM Method D 1343) using the solution density for Formula A as stated in ASTM Method D 817 (20% Cellulose ester, 72% acetone, 8% ethyl alcohol).

#### Comments

Properties reported here are typical of average lots. Eastman makes no representation that the material in any particular shipment will conform exactly to the values given.

*Eastman and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.*